

**NORDIC WOOD PRESERVATION COUNCIL – NWPC**

Technical Expert Group  
 c/o Danish Technological Institute  
 Att. Niels Morsing  
 Gregersensvej, DK 2630 Taastrup, Denmark  
 Phone: +45 72 20 23 12  
 E-mail: nmo@teknologisk.dk



Date: 2024-01-01

List no. 104

## Wood preservatives and other wood protection systems approved by the Nordic Wood Preservation Council\*\*\*

Wood preservative	Retention requirement* in <i>Pinus spp</i> sapwood, kg/m <sup>3</sup> Class**				Approval valid until	Certificate No
	M	A	AB	B		
	<b>WATER-BORNE TYPE</b>					
<b>CB + triazole products</b>						
Tanalith E3463/E3475	-	20.0	10.0	-	2028-12-31	200
Bochemit Forte Profi	-	20.0	14.0	-	2027-12-31	205
Impra ACA	-	20.0	14.0	-	2028-12-31	210
<b>ACQ products</b>						
Impralit-ACQ 1900	-	36.0	19.0	-	2027-12-31	87
Impralit-ACQ 2200	-	22.0	12.0	-	2025-12-31	175
Celcure AC 500	-	22.0	12.0	-	2025-12-31	183
impralit-KDS 4	-	28.0	15.0	-	2025-12-31	154
Impralit-KDS	-	14.0	8.0	-	2025-12-31	203
Korasit KS2	-	20.0	12.0	-	2025-12-31	204
<b>Micronized copper</b>						
Celcure MC-T3	-		5.0	-	2025-12-31	207
Celcure MC-T4	-	11.0	6.0	-	2026-12-31	209
Celcure M65	-	22.0	10.0	-	2024-12-31	202
<b>Quaternary ammonium products</b>						
Impralit-BKD	-	-	10.0	-	2025-12-31	171
<b>Triazole products</b>						
Wolsit KD-10	-	-	5.0	3.5	2027-12-31	185
<b>Other water-borne products</b>						
Wolmanit CX-8	-	18.0	9.0	9.0	2025-12-31	162
Wolmanit CX-8N	-	18.0	9.0		2027-12-31	199
Wolmanit CX-8WB	-	18.0	9.0		2025-12-31	191
Wolmanit CX-10	-	15.0	7.0	7.0	2025-12-31	176

\* The retention figure refers to the formulation specified by the preservative manufacturer.

\*\* The Nordic wood preservation classes M, A, AB and B correspond to hazard classes 5, 4 and 3 (class B is intended for external joinery) respectively according to EN 335.

\*\*\* Wood protection systems are approved according to the NWPC approval system. The approval according to BPR (Biocidal Products Regulation) is done by the European and national authorities. NWPC do not take any responsibility with respect to the BPR approval.

Wood preservative	Retention requirement* in <i>Pinus spp</i> sapwood, kg/m <sup>3</sup> Class**				Approval valid until	Certificate No
	M	A	AB	B		
<b>ORGANIC SOLVENT TYPE</b>						
<b>Triazole products<sup>¤</sup></b>						
Protim P-Vac 11	-	-	-	26.0/0.41 a.i.	2025-12-31	187
<b>OTHER OIL BASED PRODUCTS</b>						
Tanasote S40		85	85		2026-12-31	208
<b>CREOSOTE OILS</b>						
Creosote grade B		110	80	-	running	EN 13991
Creosote grade C		100	70	-	running	EN 13991
<b>MODIFIED WOOD</b>						
ThermoTreat v 2.0			>170° Min 1,5 hr	>170° Min 1,5 hr	2027-12-31	206

<sup>¤</sup> The retention requirement is uptake of the formulation/active ingredients (a.i.) in kg per m<sup>3</sup> sapwood in the treated zone.