

NORDIC WOOD PRESERVATION COUNCIL – NWPC

Technical Expert Group
c/o Danish Technological Institute
Att. Niels Morsing
Gregersensvej, DK 2630 Taastrup, Denmark
Phone: +45 72 20 23 12
E-mail: nmo@teknologisk.dk



Date: 2025-01-01
List no. 105

Wood preservatives and other wood protection systems approved by the Nordic Wood Preservation Council***

Wood preservative	Retention requirement* in <i>Pinus spp</i> sapwood, kg/m³ Class**				Approval valid until	Certificate No
	M	A	AB	B		
WATER-BORNE TYPE						
CB + triazole products						
Tanalith E3463/E3475	-	20.0	10.0	-	2028-12-31	200
Bochemit Forte Profi		20.0	14.0	-	2027-12-31	205
Impralit ACA	-	20.0	14.0	-	2028-12-31	210
ACQ products						
Impralit-ACQ 1900	-	36.0	19.0	-	2027-12-31	87
Impralit-ACQ 2200	-	22.0	12.0	-	2025-12-31	175
Impralit-ACQ 2100	-	18.0	11.0	-	2029-12-31	211
Celcure AC 500	-	22.0	12.0	-	2025-12-31	183
Celcure C65	-	18.0	9.0	-	2029-12-31	212
impralit-KDS 4	-	28.0	15.0	-	2025-12-31	154
Impralit-KDS	-	14.0	8.0	-	2025-12-31	203
Korasit KS2	-	19.0	10.0	-	2025-12-31	204
Tanalith E9850	-	18.0	9.0	-	2029-12-31	213
Micronized copper						
Celcure MC-T3	-		5.0	-	2025-12-31	207
Celcure MC-T4	-	11.0	6.0	-	2026-12-31	209
Celcure M65	-	22.0	10.0	-	2024-12-31	202
Quaternary ammonium products						
Impralit-BKD	-	-	10.0	-	2025-12-31	171
Triazole products						
Wolsit KD-10	-	-	5.0	3.5	2027-12-31	185
Other water-borne products						
Wolmanit CX-8	-	18.0	9.0	9.0	2025-12-31	162
Wolmanit CX-8N	-	18.0	9.0		2027-12-31	199

* The retention figure refers to the formulation specified by the preservative manufacturer.

** The Nordic wood preservation classes M, A, AB and B correspond to hazard classes 5, 4 and 3 (class B is intended for external joinery) respectively according to EN 335.

*** Wood protection systems are approved according to the NWPC approval system. The approval according to BPR (Biocidal Products Regulation) is done by the European and national authorities. NWPC do not take any responsibility with respect to the BPR approval.

Wood preservative	Retention requirement* in <i>Pinus spp</i> sapwood, kg/m ³ Class**				Approval valid until	Certificate No
	M	A	AB	B		
Wolmanit CX-8WB	-	18.0	9.0		2025-12-31	191
Wolmanit CX-10		15.0	7.0	7.0	2025-12-31	176
ORGANIC SOLVENT TYPE						
Triazole products^a						
Protim P-Vac 11	-	-	-	26.0/0.41 a.i.	2025-12-31	187
OTHER OIL BASED PRODUCTS						
Tanasote S40		85	85		2026-12-31	208
CREOSOTE OILS						
Creosote grade B		110	80	-	running	EN 13991
Creosote grade C		100	70	-	running	EN 13991
MODIFIED WOOD						
ThermoTreat v 2.0			>170° Min 1,5 hr	>170° Min 1,5 hr	2027-12-31	206

^a The retention requirement is uptake of the formulation/active ingredients (a.i.) in kg per m³ sapwood in the treated zone.