

NORDIC WOOD PRESERVATION COUNCIL – NWPC

Technical Expert Group
 c/o Norsk Treteknisk Institutt
 P.O. Box 113 Blindern
 NO-0314 Oslo, Norway
 Tel: +47 22 96 56 55, Fax +47 22 60 42 91
 E-mail: NTR-T@treteknisk.no



January 1 2009

List no 79

Wood preservatives approved by the Nordic Wood Preservation Council

Wood preservative	Retention requirement* in <i>Pinus spp</i> sapwood, kg/m ³ Class**				Approval valid until	Certificate No
	M	A	AB	B		
WATER-BORNE TYPE						
CCA products						
OK-K33 type C [#]	24.0	12.0	-	-	2009-12-31	79
CCP products						
Kemwood KCP Flytande	60.0 ^{##}	30.0	30.0	-	2010-12-31	122
Celcure P50 Flytande	60.0 ^{##}	30.0	-	-	2012-12-31	3
CC products						
Kemwood KC 73	-	10.0	10.0	-	2013-12-31	11
Korasit KC-s	26.0 ^{##}	19.0	-	-	2012-12-31	186
Tanalith CC oxide 3403 ^{##}	26.0 ^{##}	18.0	-	-	2009-12-31	98
CB + triazole products						
Tanalith E/Tanalith E 3491	-	18.0	13.0	-	2011-12-31	165
Tanalith E-7/Tanalith E 3492	-	16.0	8.0	-	2009-12-31	168
ACQ products						
Kemwood ACQ 1900	-	36.0	19.0	-	2012-12-31	87
Celcure AC 800	-	36.0	19.0	19.0	2012-12-31	181
ACQ 2200	-	-	12.0	-	2009-12-31	175
Celcure AC 500	-	-	12.0	-	2009-12-31	183
Quaternary ammonium products						
Mitrol C 800	-	-	8.0	8.0	2009-12-31	66
impralit-BKD	-	-	8.0	-	2009-12-31	171
Triazole products						
Gori pres 10	-	-	3.0	-	2009-12-31	137
Scanimp KF	-	-	5.2	5.2	2009-12-31	156
Celcure E41-600	-	-	8.0	-	2013-12-31	184
Wolsit KD-10	-	-	11.0	3.5	2012-12-31	185
Tanalith M 6300	-	-	14.0	-	2010-12-31	188

* The retention figure refers to the formulation specified by the preservative manufacturer.

** The Nordic wood preservation classes M, A, AB and B correspond to hazard classes 5, 4 and 3 (class B is intended for external joinery) respectively according to EN 335.

Arsenic (and therefore CCA-preservatives) is banned used within the EU and the EEA countries.

Chromium containing preservatives is not allowed in seawater in EU and EEA countries.

Wood preservative	Retention requirement* in <i>Pinus spp</i> sapwood, kg/m ³				Approval valid until	Certificate No
	Class**					
	M	A	AB	B		
Other water-borne products						
impralit-KDS 4	-	50.0	12.0	-	2009-12-31	154
Sinesto B	-	-	18.0	18.0	2009-12-31	166
Wolmanit CX-8	-	22.0	11.0	11.0	2009-12-31	162
Wolmanit CX-8 WB	-	22.0	9.0	-	2012-12-31	191
Wolmanit CX-10	-	18.0	9.0	9.0	2009-12-31	176
Wolmanit CX-SC	-	-	6.0	-	2009-12-31	173
ORGANIC SOLVENT TYPE						
Triazole products[‡]						
Protim P-vac	-	-	-	35.0/0.41 a.i.	2009-12-31	161
Protim P-Vac 11	-	-	-	26.0/0.41 a.i.	2009-12-31	187
Protim P-Vac 111	-	-	-	26.0/0.42 a.i.	2013-12-31	192
Vacsol 2162	-	-	-	26.0/0.51 a.i.	2009-12-31	158
Konvac 6106-2026	-	-	-	26.0/0.51 a.i.	2009-12-31	160
Triazole + IPBC products[‡]						
Gori vac TH92	-	-	-	30.0/0.30 a.i.	2009-12-31	138
Gori 605	-	-	-	23.0/0.23 a.i.	2010-12-31	189
Resistol	-	-	-	26.0/0.24 a.i.	2009-12-31	159
Resistol N	-	-	-	34.0/0.24 a.i.	2009-12-31	190
CREOSOTE OILS						
Creosote grade A	400	120	80	-	2009-12-31	EN 13991
Creosote grade B	400	110	80	-	2009-12-31	EN 13991
Creosote grade C	400	100	70	-	2009-12-31	EN 13991
MT-kreosot	400	110	80	-	2012-12-31	134

* The retention figure refers to the formulation specified by the preservative manufacturer.

** The Nordic wood preservation classes M, A, AB and B correspond to hazard classes 5, 4 and 3 (class B is intended for external joinery) respectively according to EN 335.

‡ The retention requirement is uptake of the formulation/active ingredients (a.i.) in kg per m³ sapwood in the treated zone.