



12 January 2004

No 70

Wood preservatives approved by the Nordic Wood Preservation Council

Wood preservative	Retention requirement* in <i>Pinus</i> spp sapwood, kg/m ³				Approval valid until	Certificate No
	Class**					
	M	A	AB	B		
WATER-BORNE TYPE						
CCA products						
Celcure CCA Type C 50%#	24,0	12,0	5,0	-	2006-12-31	126
Kemwood K33 C conc#	24,0	12,0	5,0	-	2004-12-31	153
Kemwood K33 type C#	24,0	12,0	5,0	-	2004-12-31	9
OK-K33 type C#	24,0	12,0	5,0	5,0	2004-12-31	79
Celcure CCA Type C 60%#	24,0	12,0	5,0	-	2007-12-31	170
Tanalith C 3310/Tanalith COL#	30,0	15,0	7,0	-	2004-12-31	147
Tanalith CCA oxide type C#	24,0	12,0	5,0	-	2004-12-31	17
CCB products						
Celcure CCB 90	44,0	24,0	18,0	-	2007-12-31	124
CCP products						
Kemwood KCP Flytande	-	30,0	30,0	-	2005-12-31	122
Celcure P50 Flytande	-	30,0	30,0	-	2007-12-31	3
Tanalith 3420 CCP/Tanalith CCP	-	18,0	18,0	-	2004-12-31	109
CC products						
Kemwood KC 73#	-	10,0	10,0	-	2008-12-31	11
Korasit KC-s	26,0	19,0	-	-	2007-12-31	186
Celcure O oxide	-	18,0	-	-	2008-12-31	112
CB + triazole products						
Tanalith E/Tanalith E 3491	-	18,0	13,0	-	2006-12-31	165
Tanalith E-7/Tanalith E 3492	-	18,0	9,0	-	2004-12-31	168
Tanalith EK 3496	-	-	8,0	-	2004-12-31	182
Wolmanit CX-067	-	-	7,5	7,5	2004-12-31	163
Wolmanit CT	-	18,0	13,0	-	2005-12-31	180

* The retention figure refers to the formulation specified by the preservative manufacturer.

** The Nordic wood preservation classes M, A, AB and B correspond to hazard classes 5, 4 and 3 (class B is intended for external joinery) respectively according to EN 335.

A treatment according to class A with this preservative and a subsequent treatment with creosote according to class A will give a product approved for class M.

Wood preservative	Retention requirement* in <i>Pinus</i> spp sapwood, kg/m ³				Approval valid until	Certificate No
	Class**					
	M	A	AB	B		
ACQ products						
Kemwood ACQ 1900	-	36,0	19,0	19,0	2007-12-31	87
Celcure AC 800	-	36,0	19,0	19,0	2005-12-31	181
ACQ 2200	-	-	12,0	-	2004-12-31	175
Celcure AC 500	-	-	12,0	-	2004-12-31	183
Quaternary ammonium products						
Basilit KD	-	-	12,0	-	2004-12-31	116
Mitrol C 800	-	-	8,0	8,0	2004-12-31	66
Triazole products						
Gori pres 10	-	-	3,0	-	2004-12-31	137
Gori pres 20	-	-	5,0	-	2004-12-31	123
Scanimp KF	-	-	5,2	5,2	2004-12-31	156
Scanimp KI	-	-	5,2	5,2	2004-12-31	157
Celcure E41-600	-	-	8,0	-	2004-12-31	184
Wolsit KD-10	-	-	11,0	3,5	2004-12-31	185
Other water-borne products						
Impralit-KDS 4	-	-	12,0	-	2004-12-31	154
Sinesto B	-	-	18,0	18,0	2004-12-31	166
Wolmanit CX-S	-	-	4,0	4,0	2004-12-31	121
Wolmanit CX-SD	-	-	6,0	6,0	2004-12-31	145
Wolmanit CX-070	-	-	7,0	7,0	2004-12-31	164
Wolmanit CX-8	-	-	12,0	12,0	2004-12-31	162
Wolmanit CX-10	-	-	10,0	10,0	2004-12-31	176
Wolmanit CX-SC	-	-	6,0	-	2004-12-31	173
Wolmanit CX-E	-	21,0	-	-	2005-12-31	178
Wolmanit CX-E 87%	-	24,0	-	-	2005-12-31	179
ORGANIC SOLVENT TYPE						
Organotin products						
Vacsol 2151	-	-	-	26,0	2004-12-31	106
Vacsol 2157	-	-	-	26,0	2004-12-31	128
Vacsol 2159	-	-	-	26,0	2004-12-31	130
Triazole products						
Gori vac TH102	-	-	-	24,0	2004-12-31	150
Protim P-vac	-	-	-	35,0	2004-12-31	161
Vacsol 2162	-	-	-	26,0	2004-12-31	158
Konvac 6106-2026	-	-	-	26,0	2004-12-31	160

* The retention figure refers to the formulation specified by the preservative manufacturer.

** The Nordic wood preservation classes M, A, AB and B correspond to hazard classes 5, 4 and 3 (class B is intended for external joinery) respectively according to EN 335.

Wood preservative	Retention requirement* in <i>Pinus</i> spp sapwood, kg/m ³				Approval valid until	Certificate No
	Class**					
	M	A	AB	B		
Triazole + IPBC products						
Gori vac TL93	-	-	-	30,0	2004-12-31	155
Gori vac TH92	-	-	-	30,0	2004-12-31	138
Gori vac TH94	-	-	-	24,0	2004-12-31	174
Gori vac TH 100	-	-	-	30,0	2004-12-31	177
Resistol	-	-	-	26,0	2004-12-31	159
Resistol 35	-	-	-	35,0	2004-12-31	169
CREOSOTE OILS						
Creosote oil, Scandinavian spec.	400	135	90	-	2007-12-31	-
Creosote oil, WEI type A/type B	400	135	90	-	2004-12-31	-
MT-kreosot	400	135	90	-	2007-12-31	134
VfT Impregnating Oil WEI type C	-	135	70	-	2007-12-31	167

* The retention figure refers to the formulation specified by the preservative manufacturer.

** The Nordic wood preservation classes M, A, AB and B correspond to hazard classes 5, 4 and 3 (class B is intended for external joinery) respectively according to EN 335.